





METALTEC MIRAFORM V 6/2

Product Code: NEAT058 | Revision: 20240821



Light vanishing oil for forming operations.

Available Pack Sizes







Applications

A conventional vanishing oil free from sulphur and chlorine, particularly suited to the stamping and pressing of ferrous and non-ferrous components. It is a colourless and odourless liquid which evaporates rapidly to leave a thin lubricating film, removing the need for degreasing.

Recommended by Aztec Oils as suitable for the following applications

Effective on light pressing, blanking and drawing operations on both ferrous and non-ferrous metals. Apply by pump, brush, swab or spray.

Benefits

- Chlorine and sulphur free.
- · Evaporates quickly.
- · Odourless.
- · No residual film.
- · Provides effective lubrication.

Typical Test Data		
Density @ 15°C (kg/m³)	ASTM D4052	0.81
Flash Point (°C)	ASTM D92	61
Kinematic Viscosity @ 40°C (mm ² /s)	ASTM D445	2

The typical test data provided is taken from average values, there will be some variability in production and therefore do not constitute a specification.

Recommendations

- A Safety Data Sheet is available for consultation at www.aztecoils.co.uk.
- Before using the product, it is advised to consult the Metal Working Fluids section of the Government HSE website.
- Packaging should not be left exposed to elements and drums should be laid horizontally to prevent contamination.
- This product should not be stored at temperatures over 60°C, kept out of direct sunlight, protected from frost and fluctuations in temperature.
- When disposing of the product after use, please protect the environment and comply with local regulations.

In line with our policy of continued improvement, Aztec Oils reserve the right to change specifications and availability without prior notice. This product, used according to our recommendations and for its designed application, does not represent any particular risk. The information present in this technical data sheet is indicative of the product and is given in good faith, but should not form part of any specification.