





# MANUTEC SEWING MACHINE OIL

Product Code: SPE004 | Revision: 20240821



Low viscosity & non-staining lubricating oil.

## Applications

A premium quality solvent refined paraffinic mineral oil which has a naturally high viscosity index for both industrial and domestic sewing machines. It is non-corrosive and possesses excellent chemical and thermal stability to provide high oxidation resistance with low carbon forming tendencies.

Recommended by Aztec Oils as suitable for the following applications

Suitable for all types of general lubricating needs ranging from intermittently applied total loss systems to occasional manual application.

#### **Benefits**

- · Ash free and low carbon forming tendencies.
- Clear and colourless appearance.
- · Excellent chemical and thermal stability.
- · Non-corrosive.
- · Non-staining & low aromaticity

#### **Available Pack Sizes**

Typical Test Data		
Appearance		Water white/clear oil
Density @ 15°C (kg/m³)	ASTM D4052	0.85
Flash Point (°C)	ASTM D92	>160
Kinematic Viscosity @ 40°C (mm <sup>2</sup> /s)	ASTM D445	15

The typical test data provided is taken from average values, there will be some variability in production and therefore do not constitute a specification.

### Health, Safety & Recommendations

- A Safety Data Sheet is available for consultation at www.aztecoils.co.uk.
- Packaging should not be left exposed to elements and drums should be laid horizontally to prevent contamination.
- This product should not be stored at temperatures over 60°C, kept out of direct sunlight, protected from frost and fluctuations in temperature.
- When disposing of the product after use, please protect the environment and comply with local regulations.

In line with our policy of continued improvement, Aztec Oils reserve the right to change specifications and availability without prior notice. This product, used according to our recommendations and for its designed application, does not represent any particular risk. The information present in this technical data sheet is indicative of the product and is given in good faith, but should not form part of any specification.